PRODUCT SPECIFICATION SHEET

CG8-BL-HP

STRONG ACID CATION

HIGH-PURITY GRADE
BLACK POLYSTYRENIC GEL
8% CROSSLINKED
SODIUM FORM

ResinTech CG8-BL-HP is a high purity strong acid cation resin in sodium form. It is dark brown in color and made from a 8% cross-linked gel. The HP (high purity) designation means it is Gold Seal Certified by the WQA for use in potable water applications. CG8-BL-HP is intended for softening and other salt form applications that require potable water certification.

APPLICATIONS

- Softening Municipal
- Softening Residential



TYPICAL PROPERTIES & PHYSICAL CHARACTERISTICS	
Polymer Matrix	Styrenic Gel
Ionic Form	Sodium
Functional Group	Sulfonic Acid
Physical Form	Spherical Beads
Particle Size	16 to 50 US Mesh (297 - 1190 µm)
% < 50 mesh (300μm)	< 1%
Minimum Sphericity	93%
Uniformity Coefficient	1.6
Reversible Swelling	Na to H 5% to 9%
Temp Limit	280°F (138°C)
Capacity (meq/mL)	2.0
Moisture Retention	42% to 49%
Shipping Weight	51 - 53 lbs/ft³ (817 - 849 g/L)
Color	Dark Brown to Black
Regenerability	Yes

CERTIFICATIONS

- WQA Gold Seal*
- Kosher Certified
- FDA Compliance**

PACKAGING OPTIONS

- 1 ft³ bags
- 1 ft³ boxes
- 1 ft³ drums
- 7 ft³ drums
- 42 ft³ supersacks

Revision 1.3 ResinTech, Inc.®




^{*} NSF/ANSI/CAN 61: Drinking Water System Components - Health Effects


^{**} Paragraph 21CFR173.25 of the Food Additives Regulations of the US FDA

CG8-BL-HP

STRONG ACID CATION

HIGH-PURITY GRADE BLACK POLYSTYRENIC GEL 8% CROSSLINKED SODIUM FORM





IRON REMOVAL

100

80

60

40

20

n

0.0

Percent of Expansion

40°F

60°F


80°F 100°F

CG8-BL-HP has good capacity for ferrous iron. Iron content in the feedwater should not be more than 1 mg/L Fe per each 17 mg/L of hardness.

gpm / sq.ft.

AMMONIA REMOVAL

CG8-BL-HP is slightly selective for ammonia compared to sodium but hardness is much more preferred. Ammonia is not ionized at pH above 9 and is not well removed when the pH is significantly alkaline.



Capacity and leakage data are based on the following: 2:1 Ca:Mg ratio, 500 ppm TDS as CaCO₃, 0.2% hardness in the salt and 10% brine concentration applied co-currently through the resin over 30 minutes. No engineering downgrade has been applied.

SUGGESTED OPERATING CONDITIONS

Maximum continuous temperature
Sodium form

280°F

Minimum bed depth
24 inches

Backwash expansion
25 to 50 percent

Maximum pressure loss
25 psi

Operating pH range
0 to 14 SU

Regenerant Concentration

Regenerant Concentration 5 to 10 percent HCI Hydrogen cycle 1 to 8 percent H₂SO₄ Hydrogen cycle 10 to 15 percent NaCl Salt cycle Regenerant level 4 to 15 lbs./cu.ft. 0.5 to 1.5 gpm/cu.ft. Regenerant flow rate >20 minutes Regenerant contact time Same as dilution water Displacement flow rate 10 to 15 gallons/cu.ft. Displacement volume Same as service flow Rinse flow rate 35 to 60 gallons/cu.ft. Rinse volume 1 to 10 gpm/cu.ft. Service flow rate

Note: These guidelines describe average low risk operating conditions. They are not intended to be absolute minimums or maximums.

For operation outside these guidelines, contact ResinTech Technical Support

Revision 1.3
ResinTech, Inc.®

