PRODUCT SPECIFICATION SHEET



BLACK POLYSTYRENIC GEL 8% CROSSLINKED SODIUM FORM

ResinTech CG8-BL is a dark-colored strong acid cation resin in sodium form made from a 8% cross-linked gel. CG8-BL has the same physical characteristics, regeneration efficiency, and oxidative stability as other resins in the CG8 family. CG8-BL is intended for use in all industrial applications including both softening and demineralization and is recommended for mixed beds where its dark color distinguishes it from amber-colored anion resins.

APPLICATIONS

- Softening Industrial
- Demineralization
- Iron Removal
- Ammonia Removal

TYPICAL PROPERTIES & PHYSICAL CHARACTERISTICS	
Polymer Matrix	Styrenic Gel
Ionic Form	Sodium
Functional Group	Sulfonic Acid
Physical Form	Spherical Beads
Particle Size	16 to 50 US Mesh (297 - 1190 μm)
% < 50 mesh (300μm)	< 1%
Minimum Sphericity	93%
Uniformity Coefficient	1.6
Reversible Swelling	Na to H 5% to 9%
Temp Limit	280°F (138°C)
Capacity (meq/mL)	2.0
Moisture Retention	42% to 49%
Shipping Weight	51 - 53 lbs/ft³ (817 - 849 g/L)
Color	Dark Brown to Black
Regenerability	Yes

CERTIFICATIONS

- Kosher Certified
- Halal Certified
- FDA Compliance*

PACKAGING OPTIONS

- 1 ft³ bags
- 1 ft3 boxes
- 1 ft³ drums
- 7 ft³ drums
- 42 ft³ supersacks





Revision 1.2 ResinTech, Inc.®

^{*} Paragraph 21CFR173.25 of the Food Additives Regulations of the US FDA



BLACK POLYSTYRENIC GEL 8% CROSSLINKED SODIUM FORM






IRON REMOVAL

CG8-BL has good capacity for ferrous iron. Iron content in the feedwater should not be more than 1 mg/L Fe per each 17 mg/L of hardness.

AMMONIA REMOVAL

CG8-BL is slightly selective for ammonia compared to sodium but hardness is much more preferred. Ammonia is not ionized at pH above 9 and is not well removed when the pH is significantly alkaline.



Capacity and leakage data are based on the following: 2:1 Ca:Mg ratio, 500 ppm TDS as CaCO₃, 0.2% hardness in the salt and 10% brine concentration applied co-currently through the resin over 30 minutes. No engineering downgrade has been applied.

SUGGESTED OPERATING CONDITIONS

Maximum continuous temperature
Sodium form
280°F

Minimum bed depth
24 inches

Backwash expansion
25 to 50 percent

Maximum pressure loss
25 psi

Operating pH range
0 to 14 SU

Regenerant Concentration
Hydrogen cycle
5 to 10 percent HCI

1 to 8 percent H₂SO₄ Hydrogen cycle 10 to 15 percent NaCl Salt cycle Regenerant level 4 to 15 lbs./cu.ft. 0.5 to 1.5 gpm/cu.ft. Regenerant flow rate >20 minutes Regenerant contact time Same as dilution water Displacement flow rate 10 to 15 gallons/cu.ft. Displacement volume Same as service flow Rinse flow rate 35 to 60 gallons/cu.ft. Rinse volume 1 to 10 gpm/cu.ft. Service flow rate

Note: These guidelines describe average low risk operating conditions. They are not intended to be absolute minimums or maximums.

For operation outside these guidelines, contact ResinTech Technical Support

Revision 1.2
ResinTech, Inc.®

